


## Appendix J

### CE marking information for modular tiles

 Year: 2009	Reference standard: EN 12057:2004 Product: Modular tiles End uses: Internal & external wall, ceiling finishes and flooring	
XIAMEN JINGYUE STONE INDUSTRIAL CO., LTD 7D, XINGHU COMMERCIAL BUILDING, 46# HULI ROAD, XIAMEN, P.R. CHINA		
List of the characteristics	Declared values	Test method
Denomination	Tradition name: G603 Petrological family: FINE GRAIN QUARTZ DIORITE Typical colour: Grey Place of origin: Jinjiang Fujian China	EN 12440:2000 EN 12407:2007
Reaction to fire	Class A1 <sub>fl</sub>	Without testing (see Decision 96/603/EC, as amended)
Water absorption at atmospheric pressure	≤0.3%	EN 13755:2002
Flexural strength	≥13MPa	EN 12372:2006
Frost resistance	Change in mean flexural strength after 48 cycles frosting: ≤10%	EN 12371:2001
Thermal shock resistance	No performance determined	EN 14066:2003
Slip resistance Testing surface:sawn face	SRV dry: ≥70unit SRV wet: ≥60unit	EN 14231:2003
Apparent density	2640kg/m <sup>3</sup>	EN 1936:2006
Open porosity	1.1%	EN 1936:2006
Abrasion resistance Testing surface:sawn face	≤18mm	EN 14157:2004 method A

Test report form No.: SGS-XMML-stone-V2.0

This document is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at [http://www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not operate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. This document cannot be reproduced except in full, without prior approval of the Company.